

## SPECIFICATIONS:

General Features	Model Name	Permeate Flow Rate GPD (L/day)	Molecular Weight Cut Off (MWCO)
	<b>UE1810</b>	<b>200 (757)</b>	<b>100K</b>
	<b>UE1812</b>	<b>250 (946)</b>	<b>100K</b>
	<b>UE2010</b>	<b>450 (1,703)</b>	<b>100K</b>

1. The stated product performance is based on data taken after 30 minutes of operation at the following test conditions:

- Pure water (2 MQ) at 20psig applied pressure
- 100% recovery
- 77 °F (25 °C)


2. Permeate flow rate for each element may vary +15/ -15%.

3. Elements can be supplied as dry or wet-type. Wet-tested elements are soaked in a preservative solution (1.0% food grade SBS) and vacuum sealed in a poly bag. All elements are individually boxed.

**Membrane type:** Thin-Film Composite  
**Membrane material:** Polyamide (PA)  
**Element configuration:** Spiral-Wound, Tape Wrapping

## Dimensions

Model Name	A	B	C	D	E
<b>UE1810</b>	0.67 inch (17mm)	0.55 inch (14mm)	10.08 inch (256 mm)	0.98 inch (25 mm)	1.77 inch (45 mm)
<b>UE1812</b>	0.67 inch (17mm)	0.87 inch (22mm)	11.73 inch (298 mm)	0.87 inch (22 mm)	1.77 inch (45 mm)
<b>UE2010</b>	0.67 inch (17mm)	0.55 inch (14 mm)	11.73 inch (298 mm)	0.98 inch (25 mm)	1.89 inch (48 mm)



Toray Chemical Korea Inc.

## APPLICATION DATA:

### Operating Limits

· Max. Operating Pressure	125 psi (0.86 MPa)
· Max. Feed Flow Rate	2 gpm (0.45 m <sup>3</sup> /hr)
· Max. Operating Temperature	113 °F (45 °C)
· Operating pH Range	3.0–10.0
· Max. Turbidity	1.0 NTU
· Max. SDI (15 min)	5.0

The information provided in this document is solely for informative purposes. It is the user's responsibility to ensure the appropriate usage of this product. Toray Chemical Korea Inc. assumes no obligation, liability or damages incurred for the misuse of the product or for the information provided in this document. This document does not express or implies any warranty as to the merchantability or fitness of the product.

## GENERAL HANDLING PROCEDURES

- Elements contained in the boxes must be kept dry at room temperature (7–32°C; 40–95°F) and should not be stored in direct sunlight.
- When running the system for the first time, the permeate should be discarded continuously at least 15 minutes.
- Keep elements moistly at all times after initial wetting.
- Elements should be immersed in a preservative solution during storage, shipping and system shutdowns to prevent biological growth and freezing. The standard storage solution contains 1% by weight sodium bisulfite or sodium metabisulfite (food grade). For short term storage (i.e. one week or less) 1% by weight sodium metabisulfite solution is adequate for preventing from biological growth.
- Keep elements moistly at all times after initial wetting.
- Only use chemicals compatible with the membrane elements and components. Use of such chemicals may void the element limited warranty. For additional information on use of approved chemicals please contact your nearest CSM representative.
- Permeate pressure must always be equal or less than the feed/concentrate pressure. Damage caused by permeate back pressure voids the element limited warranty.

**Toray Chemical Korea Inc.**

For more information on our products, company and regional contacts, please visit our website at [www.csmfilter.com](http://www.csmfilter.com).

Product Specification Sheet / Model UE1810, UE1812, UE2010

Page 2 of 2

Rev. 3.1, November 2017