

SPECIFICATIONS

Title	Cation exchange membrane	Anion exchange membrane
Characteristics	Standard	
Functional Group	Sulfonic acid	Ammonium
Counter Ion	Na ⁺	Cl ⁻
Resistance ($\Omega \cdot \text{cm}^2$)	< 2.5	< 2.5
Transport Number	> 98	> 95
Burst Strength (MPa)	> 0.4	
Thickness (μm)	57 - 63	
Reinforcement	Polyolefin	
Operating Temperature($^{\circ}\text{C}$)	< 60	
pH	1-14	2-12

The values in these tables from the laboratory and are not guaranteed values.

The data published in this sheet are subject to change without notice.