RE4040-FEn

Enhanced fouling resistant RO element for brackish water and wastewater reuse

- Fouling resistant
- High Permeate Flow and High Rejection
- Robustness and High Durability in a wide pH



SPECIFICATIONS


General Features

Permeate Flow Rate	2,400 GPD (9.1 m^3/day)
Nominal Salt Rejection	99.7% (Minimum 99.4%)
Effective Membrane Area	85ft^2 (7.9 m^2)
Membrane Type	Thin-Film Composite
Membrane Material	Polyamide (PA)
Element Configuration	Spiral-Wound, FRP Wrapping

Test Conditions: 2,000 mg/L NaCl solution at 225 psig (1.55 MPa) applied pressure; 15% recovery; 77℉(25℃); pH 6.5–7.0; Permeate flow rate for each element may vary but will be no more than +25 / -15%.

Dimensions and Weight

Model Name	A	B	C	D/E	Part Number	
					Inter-Connector	Brine Seal
RE4040-FEn	40.0 inch (1,016 mm)	3.9 inch (99.0 mm)	0.75 inch (19.1 mm)	1.05 inch (26.7 mm)	SWA01050	SWA01046



1. Each membrane element supplied with one interconnector (coupler) and four O-rings.
2. All RE4040 elements fit nominal 4.0 inch (101.6 mm) I.D. pressure vessels.

RE4040-FEn

Enhanced fouling resistant RO element for brackish water and wastewater reuse

APPLICATION DATA

Operating Limits

Max. Pressure Drop / Element	15 psi (0.10 MPa)
Max. Pressure Drop / 240" Vessel	60 psi (0.41 MPa)
Max. Operating Pressure	600 psi (4.14 MPa)
Max. Feed Flow Rate	18 gpm (4.09 m^3/hr)
Min. Concentrate Flow Rate	4 gpm (0.91 m^3/hr)
Max. Operating Temperature	113°F (45°C)
Operating pH Range	2.0 – 11.0
CIP pH Range	1.0 – 13.0
Max. Turbidity	1.0 NTU
Max. SDI (15 min)	5.0
Max. Chlorine Concentration	< 0.1 mg/L

GENERAL HANDLING PROCEDURES

- Elements contained in the boxes must be kept dry at room temperature (7–32°C; 40–95°F) and should not be stored in direct sunlight.
- For WET-TYPE, the preservative solution (1% sodium metabisulfite solution) is added to prohibit the growth of micro-organisms.
- Permeate from the first hour of operation should be discarded.
- Salt rejection would be stabilized within 48 hours of continuous operation depending on feedwater and operating conditions, but may take over a week for dry elements.
- Keep elements moist at all times after initial wetting.
- Avoid excessive pressure and flow spikes.
- Only use chemicals compatible with the membrane elements and components. Use of such chemicals may void the element limited warranty.
- Permeate pressure must always be equal or less than the feed/concentrate pressure. Damage caused by permeate back pressure voids the element limited warranty.
- The element shell is FRP(Fiber Reinforced Plastic). Be aware of glass fiber strands and use safety equipment.